



Understanding Experiments: the Power of First Principle Simulations of Metal-Organic Frameworks



Danny E. P. Vanpoucke,^{1,2} Kevin Hendrickx,^{1,2} Bart Beuken,³ Dirk De Vos,³
Karen Hemelsoet,¹ Pascal Van Der Voort² & Veronique Van Speybroeck¹

¹Center for Molecular Modeling, Ghent University, Technologiepark 903, 9052 Zwijnaarde, Belgium

²Dept. Inorganic and Physical Chemistry, Ghent University, Krijgslaan 281-S3, 9000 Ghent, Belgium

³Centre for Surface Chemistry and Catalysis, KU Leuven, Pleinlaan 2, Kasteelpark Arenberg 23, 3001 Leuven, Belgium


Old:
UiO-66(Zr)-X

Abstract


Metal-organic Frameworks (MOFs) are a versatile class of crystalline materials showing great promise in a wide range of applications. Recently light-based applications have become of interest with focus on luminescence and photocatalysis. Although new luminescent MOFs are readily synthesized, understanding of the underlying mechanisms in the electronic structure are often lacking.

First principle simulations of these MOFs can be used both for validating the model and elucidating the luminescent behavior.



New:
COK-69(Ti)



Electronic structure calculations



Orbital character analysis




Experimental validation


	PBE		HSE06		Exp. Band gap (eV)
	Band gap (eV)	Gap state width (eV)	Band gap (eV)	Gap state width (eV)	
UiO-66	2.920	-	4.030	0.100	3.97
UiO-66-OH	2.150	0.070	3.010	0.200	3.21
UiO-66-OHx2	1.350	0.100	2.150	0.220	2.54
UiO-66-SH	1.850	0.220	2.661	0.350	2.63
UiO-66-SHx2	1.331	0.230 & 0.220	2.101	0.360 & 0.350	-

Conclusion

- Functional groups modify the electronic structure through the introduction of a gap-state.
- The later originates from the π -orbital of the linker.
- The calculated band gap shows perfect agreement with the experimentally determined one.





Improve model



Check electronic structure

Bonus: Strong correlation



Experimental validation



Conclusion

- First principle simulations can be used to fine-tune the atomic scale model of the flexible photoactive MOFs like COK-69
- The blue color of the reduced COK-69 can directly be linked to the presence of Ti^{3+} species.
- To accurately describe the electronic structure of the COK-69 MOF one needs to go beyond DFT.

References:

- [1] "Understanding intrinsic light absorption properties of UiO-66 frameworks", K. Hendrickx, D.E.P. Vanpoucke, K. Leus, et al. submitted to Inorganic Chemistry
- [2] "A Flexible Photoactive Titanium MOF based on a $[TiIV3(\mu3-O)O2(COO)6]-Cluster$ ", B.Beuken, F.Vermoortele, D.E.P.Vanpoucke, et al. submitted to Angewandte Chemie
- [3] D.E.P. Vanpoucke, P. Bultinck, and I. Van Driessche, *J. Comput. Chem.* **34** 405-417 (2013) & *J. Comput. Chem.* **34** 422-427 (2013)

Logos: Belspo, IAP, FWO & VSC