

**Designing temperature-responsive flexible metal-organic frameworks by tuning the balance between dispersion and entropy**

Kurt Lejaeghere<sup>1\*</sup>, Jelle Wieme<sup>1</sup>, Georg Kresse<sup>2</sup>, Veronique Van Speybroeck<sup>1</sup>

<sup>1</sup> Center for Molecular Modeling, Ghent University, Technologiepark 46, BE-9052 Zwijnaarde, Belgium.

<sup>2</sup> Faculty of Physics and Center for Computational Materials Science, University of Vienna, Sensengasse 8/12, A-1090 Vienna, Austria.

Corresponding author: Kurt.Lejaeghere@UGent.be

**Keywords:** MIL-53; temperature-induced breathing; dispersion; entropy.

The unique combination of metal nodes and organic linkers has endowed some metal-organic frameworks (MOFs) with an unparalleled flexibility. A particularly fascinating example is MIL-53(Al). This so-called breathing framework undergoes a large and abrupt volume change as a function of temperature, switching between a narrow- and large-pore phase. However, the underlying physics has thus far remained unclear, prohibiting rational design for sensing and actuator applications.

We show that tuning the temperature-dependent phase stability of breathing MOFs results requires shifting the delicate balance between dispersion interactions and entropic effects. Dispersion favours the narrow-pore phase at low temperatures, while the high-temperature stabilization of the large-pore structure is entropy-driven. Because standard dispersion-corrected density-functional methods do not describe these aspects correctly, we present an accurate theoretical framework based on the random-phase approximation to the correlation energy, including single-excitation corrections. Many-body dispersion effects prove to be crucial to get the relative phase stability at 0 K right.

Based on insights for MIL-53(Al), the design of temperature responsivity is illustrated by means of a series of isorecticular materials. Linker substitution is found to affect the breathing capability quite drastically, while metal substitution allows more subtle tuning. Among MIL-53(Al), MIL-53(Al)-FA, DUT-4, DUT-5 and MIL-53(Ga), only MIL-53(Al) and MIL-53(Ga) were confirmed to display a phase transition within physically relevant temperature ranges.

[1] J. Wieme, K. Lejaeghere, G. Kresse, V. Van Speybroeck, "Tuning the balance between dispersion and entropy to design temperature-responsive flexible metal-organic frameworks", *Nature Communications* **9**, 4899 (2018).